



High quality semi aniline from Italy with a bright face. Our Swing range has a strong topcoat with a 20% gloss factor and is exclusive to Leather Italia. Swing is a hard-wearing, high-performance leather and is perfect for both commercial and residential projects.

TECHNICAL SPECIFICATIONS:

Horizontal burn test, wall + elevator	AS/NZS 3837
Soft furnishings burn test	AS.1530.30
Internal marine	IMO 652

Type	Semi Aniline
Size	4.5 - 5.0sqm approx.
Thickness	1.1 - 1.3mm
Country of origin	Italy
Application	Commercial, Residential + Internal Marine



Leather Italia

CARE INSTRUCTIONS:

Protect from direct sunlight, excessive heat and sharp objects. Clean with a damp cloth and Ph neutral cleaner. Do not soak leather with excessive water. Take regular care of your leather by removing any dust with either a soft brushed vacuum cleaner or damp cloth. Avoid chemical polishes and soap. Polish with a dry cloth.

**please use images as guides, for true reference please request a sample **.




havana



veludo



rusty nails



night club



passion

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTa Product Testing
A.B.N 43 006 014 106
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400 Fax (03) 9371 2499

Group Number Assessment

(In accordance with AS 5637.1-2015)

This is to confirm that the product as described below has been tested by AWTa Product Testing .

Testing was performed in accordance with AS/NZS 3837-1998 Method of test for heat and smoke release rates for materials and products using an oxygen consumption calorimeter.

Test Sponsor :	Leather Italia Building D, 60 Perry Street Matraville NSW 2036	Test Number :	18-002889
		Issue Date :	12/06/2018
		Print Date :	29/01/2019

Sponsor Product	Clients Ref : "Swing" Leather Colour : Yellow End Use : Upholstery, Wall Panelling Nominal Composition : Semianiline leather Nominal Mass per Unit Area/Density : 1.0 - 1.2mm
-----------------	--

Product Group Number Classification :	1
Average Specific Extinction Area :	17.4 m ² /kg


Chris Campbell
Client Relations Manager

28005

The message/document(s) contained in this electronic attachment is intended for the party to which it is addressed and may contain confidential information or be subject to professional privilege. Its transmission is not intended to place the contents into the public domain.

If you have received this transmission in error, its disclosure or copying is prohibited . Please contact us by collect call so that arrangements can be made at our expense to rectify the error.

TEST REPORT

Sample Description Clients Ref : "Swing"
 Leather
 Colour : Yellow
 End Use : Upholstery, Wall Panelling
 Nominal Composition : Semianiline leather
 Nominal Mass per Unit Area/Density : 1.0 - 1.2mm

AS/NZS 3837-1998 Method of Test for Heat and Smoke Release Rates for Materials and Products using an Oxygen Consumption Calorimeter

Date Tested 09/06/2018

	Specimen				
	1	2	3	Mean	
Average Heat Release Rate	32.9	21.3	26.3	26.8	kW/m ²
Average Specific extinction area	25.0	7.1	20.0	17.4	m ² /kg

(according to Specification C1.10 of the Building Code of Australia)

Test orientation : Horizontal

	Specimen				
	1	2	3	Mean	
Irradiance	50	50	50	50	kW/m ²
Exhaust flow rate	24	24	24	24	L/sec
Time to sustained flaming	43	41	38	41	sec
Test duration	420	687	598	568	sec
Peak heat release after ignition	106.9	77.3	80.6	88.3	kW/m ²
Average heat at 60 s	85.2	61.4	65.0	70.5	kW/m ²
Average heat at 180 s	48.6	41.5	44.3	44.8	kW/m ²
Average heat at 300 s	35.6	31.0	35.3	34.0	kW/m ²
Total heat released	12.5	13.8	14.8	13.7	MJ/m ²
Average effective heat of combustion	6.6	6.2	7.2	6.6	MJ/kg
Initial thickness	7.5	7.5	7.5	7.5	mm
Initial mass	91.5	91.5	85.9	89.6	g
Mass remaining	75.3	72.7	68.3	72.1	g
Mass percentage pyrolysed	17.7	20.6	20.4	19.6	%
Mass loss	16.2	18.8	17.6	17.5	g
Average rate of mass loss	5.0	3.4	3.7	4.0	g/m ² .s

Additional Observations

Difficulties Encountered during Testing

These test results relate only to the behaviour of the product under the conditions of the test, they are not intended to be the sole criterion for assessment of performance under real fire conditions.

The results of these fire tests may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of the fire hazard under all fire conditions.

Samples were loose laid onto a substrate of 6mm thick cement sheeting prior to testing.

Tests were conducted with a wire grid placed over the sample during testing. This was done to contain intumescing sample within the sample holder.

28005

© Australian Wool Testing Authority Ltd
 Copyright - All Rights Reserved




Accredited for compliance with ISO/IEC 17025 - Testing
 - Chemical Testing
 - Mechanical Testing
 - Performance & Approvals Testing

: Accreditation No. 983
 : Accreditation No. 985
 : Accreditation No. 1356



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



MICHAEL A. JACKSON B.Sc (Hons)
 MANAGING DIRECTOR

0204/11/06



www.eccolt.com.au

TEST REPORT

Client : Leather Italia
 Building D, 60 Perry Street
 Matraville NSW 2036

Test Number : 18-002890
 Issue Date : 8/06/2018
 Print Date : 30/07/2019

Sample Description

Clients Ref : "Swing"
 Leather
 Colour : Black,Maroon,Yellow
 End Use : Upholstery, Wall Panelling
 Nominal Composition : Semianiline leather
 Nominal Mass per Unit Area/Density : Approx: 695g/m²
 Nominal Thickness : 1.0 - 1.2mm

AS/NZS 1530.3-1999

Methods for Fire Tests on Building Materials, Components and Structures**Part 3: Simultaneous Determination of Ignitability,
 Flame Propagation, Heat Release and Smoke Release**

Face tested:	Face	
Date tested:	08/06/2018	
	Standard Error	Mean
Ignition time	0.49	5.29 min
Flame propagation time	Nil	Nil sec
Heat release integral	3.0	79.4 kJ/m ²
Smoke release, log d	0.0810	-1.0454
Optical density, d		0.0979 / metre
Number of specimens ignited:	6	
Number of specimens tested:	6	
Regulatory Indices:		
Ignitability Index	15	Range 0-20
Spread of Flame Index	0	Range 0-10
Heat Evolved Index	3	Range 0-10
Smoke Developed Index	4	Range 0-10

These results only apply to the specimen mounted, as described in this report. The result of this fire test may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of fire hazard under all fire conditions.

The reaction of thin unsupported flexible materials to flame impingement can be assessed in accordance with AS 1530.2. Where materials of thickness less than 2mm that are sufficiently flexible to be bent by hand around a mandrel of 2mm diameter or less are subjected to the test described herein, they should also be subjected to the test in AS 1530.2.

Each test specimen had an unattached backing of 4.5mm thick fibre reinforced cement board.

Each test specimen was restrained on the exposed face by a layer of galvanised welded square mesh made from wire of nominal diameter 0.8mm and nominal spacing 12mm in both directions and securely fixed to a backing board at four points each 100mm from the centre of the sample and the assembly clamped in four places.

To allow free movement of sample during testing all corners were folded away from the clamps.

28006

© Australian Wool Testing Authority Ltd
 Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing
- Mechanical Testing
- Performance & Approvals Testing

- : Accreditation No. 983
- : Accreditation No. 985
- : Accreditation No. 1356



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

M. Jackson
 MICHAEL A. JACKSON B.Sc.(Hons)
 MANAGING DIRECTOR

0204/11/06

APPROVED SIGNATORY



www.eccolt.com.au